



SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05016/01 Issued:20/11/2009 Reprinted: 20/11/2009 Extract Page 01

Reference : 94-3048-12

Sample Date : 09/11/2009

Serial Number : 0077

Elution Test

ELEMENT	RESULT
Ni Elution Pendant	XXXXX <0.1 Pass

SILVER PLATE OVER PEWTER

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood
 Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05016/01 Issued:20/11/2009 Reprinted: 20/11/2009 Extract Page 01

Reference : 93-0421-12

Sample Date : 09/11/2009

Serial Number : 0079

Elution Test

ELEMENT	RESULT
Ni Elution Bead	XXXXX <0.1 Pass

SILVER PLATE OVER PEWTER

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
 Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
 Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
 Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood
 Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05016/01 Issued:20/11/2009 Reprinted: 20/11/2009 Extract Page 01

Reference : 94-2300.-26

Sample Date : 09/11/2009

Serial Number : 0080

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
Pendant	0.38 Pass

SILVER PLATE OVER PEWTER

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES

A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05016/01 Issued:20/11/2009 Reprinted: 20/11/2009 Extract Page 01

Reference : 94-3055-26

Sample Date : 09/11/2009

Serial Number : 0081

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
Pendant	0.25 Pass

GOLD PLATE OVER PEWTER

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.


Report No. 05016/01 Issued: Reprinted: 20/11/2009 Extract Page 01

Reference : 94-5526-12	Sample Date : 09/11/2009	Serial Number : 0076
Elution Test		
ELEMENT	RESULT	
Ni Elution Bead	XXXXX <0.1 Pass	
SILVER PLATE OVER PEWTER		

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
 Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
 Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
 Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood
 Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05016/01 Issued:20/11/2009 Reprinted: 20/11/2009 Extract Page 01

Reference : 94-5588-12

Sample Date : 09/11/2009

Serial Number : 0078

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
Wings	0.49 Pass

SILVER PLATE OVER PEWTER

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05016/01 Issued:20/11/2009 Reprinted: 20/11/2009 Extract Page 01

Reference : 94-5713-25

Sample Date : 09/11/2009

Serial Number : 0083

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
Bead Gold	0.25 Pass

GOLD PLATE OVER PEWTER

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson

