



SHEFFIELD ANALYTICAL SERVICES
A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05023/01 Issued:20/12/2010 Reprinted: 20/12/2010 Extract Page 01

Reference : SW BLK

Sample Date : 06/12/2010

Serial Number : 0134

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
Pendant	<0.1 Pass

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES

A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05023/01 Issued:20/12/2010 Reprinted: 20/12/2010 Extract Page 01

Reference : SW BRASSOX

Sample Date : 06/12/2010

Serial Number : 0135

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
Key	<0.1 Pass

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson



Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401

Order No.



Report No. 05023/01 Issued:20/12/2010 Reprinted: 20/12/2010 Extract Page 01

Reference : SW SILVER

Sample Date : 06/12/2010

Serial Number : 0136


Elution Test


ELEMENT	RESULT
Ni Elution	XXXXX
T-Bar Ring	<0.1 Pass

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson





SHEFFIELD ANALYTICAL SERVICES

A Division of Sheffield Assay Office

Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05023/01 Issued:20/12/2010 Reprinted: 20/12/2010 Extract Page 01

Reference : RS SILVER

Sample Date : 06/12/2010

Serial Number : 0138

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
T-Bar Ring	<0.1 Pass

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson



Tierra Cast
3177 Guernville Road
Santa Rosa
California
USA
CA 95401



Order No.

Report No. 05023/01 Issued:20/12/2010 Reprinted: 20/12/2010 Extract Page 01

Reference : SW COPPER

Sample Date : 06/12/2010

Serial Number : 0139

Elution Test

ELEMENT	RESULT
Ni Elution	XXXXX
Hoop	<0.1 Pass

Elution results reported as $\mu\text{g}/\text{cm}^2/\text{week}$.
Tested to BSEN1811 inc BSEN12472 (unless stated otherwise)
Piercing assemblies Pass = $<0.2 \mu\text{g}/\text{cm}^2/\text{week}$.
Other components Pass = $<0.5 \mu\text{g}/\text{cm}^2/\text{week}$.

Signature: A.S. Team Leader- M Wood

Lab Manager - F M Hudson

